# **MESIL**®

## MESIL<sup>®</sup> ME 801

**Two Components Silicone Structural Sealant** 

#### **TECHNICAL DATA SHEET**

#### **Characteristics**

MESIL® ME801 is two components neutral high modulus structural silicone sealant for glazed curtain wall.

#### **Typical applications**

- All kinds of curtain wall structural adhesivity assembles
- Structural adhesion and sealing of insulating glass.
- Adhesion and sealing of the all kinds of spray metal materials
- Glass, Coated glass, tile and masonry, concrete, Oil-free wood

#### **Technical indexes**

No.	Test Item			Unit	Standard Value
1	Appearance			-	A white color, no crust, impurities
				-	B black color, no crust, impurities
2	Sagging	Vertical		mm	≤3
		H	orizontal	-	No deformation
3	Application time(20min)			S	≤10
4	Surface dry time			h	≤3
5	Shore hardness			Shore A	20-60
		Tensile	<b>23</b> ℃	Мра	≥0.60
6		bonding	<b>90</b> ℃		≧0.45
		strength	After water		≥0.45
	Tensile bonding		soaking		
	properties		After water		≧0.45
			ultraviolet		
	Bond damage area 23°C Maximum tensile rate		amage area	%	≦5
			%	≧100	
Rema	rk. The following spe	cifications are	tested according t	o weight rate: A	·B-12·1

Remark: The following specifications are tested according to weight rate: A:B=12:1

#### Packaging

Com A 190L/ Metal barrel; Com B 19L/ Plastic barrel, Com A 19L/ Plastic barrel; Com B 1.9L/Plastic cartridge.

### **Contact information**

Henan Minmetals East Industrial Co., Ltd. Add.: No.1159, Renmin Road, Jiaozuo City, Henan Province, P.R.China

#### **Storage**

In the dry place, the temperature shouldn't exceed 25  $^\circ\!{\rm C}$  ; The Shelf-life is : 12 months

Tel.: +86 391 3565637 Fax.: +86 391 3565657 Email: info@minmetalseast.com Website: www.mesealant.com

The data presented in this document is based on our best knowledge. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights. We reserve the right to alter product constants within the scope of technical progress or new developments. Any user of our products shall bear the full risk connected to their use including but not limited to their properties and fitness for any purpose.